

740

HEAVY DUTY RUST GUARD

APPLICATION AREAS

- Metal Tools
- · Machinery, Pipes
 - Stampings
- Pumps, Fittings, Valves
 - Roofs
 - Equipment Tanks
 - · Parts in storage



Before using this product, please refer to Safety Data Sheet (SDS).







PRODUCT DATA SHEET

KEY FEATURES AND BENEFITS

- Excellent resistance to acid, alkali and salt air fumes
- Dry wax film, does not flake or peel
- Provides up to 2 years corrosion protection under sheltered outdoor conditions
- Conforms to MIL-C-16173D Grade 1 and 4
- · Easy to apply and easy to remove

PACKAGING

Aerosol 3.8 L/1 Gallon 20 L 208 L

DIRECTIONS

The surface should be free from dirt, oil, grease, moisture, rust, lint, etc. Apply Chesterton 740 Heavy Duty Rust Guard by spray, dip or brush. Apply evenly. Observe dangers while using. Single or multiple coats may be used. Allow to dry between coats. Dries completely in 12 – 24 hours.

DESCRIPTION

Chesterton® 740 Heavy Duty Rust Guard is a premium quality corrosion preventative coating designed with user ease of application in mind. It is the perfect coating for those areas of the plant constantly exposed to humidity and corrosive fumes. It protects iron, steel, aluminum and other metals in industrial, automotive and marine applications indoors and outdoors (sheltered) for up to 2 years. A smooth, homogenous mixture, 740 Heavy Duty Rust Guard forms a waxy elastic film which heals itself when scratched or damaged. 740 Heavy Duty Rust Guard can be recoated for maximum service life. New coats can be applied over old without extensive surface preparation. It can also be applied directly over Chesterton® 763 Rust Transformer® without a water rinse for an excellent 1 – 2 barrier system. Chesterton 740 Heavy Duty Rust Guard is long lasting and durable. The tough coat deposited with even a single application approaches the performance of many paints.

TYPICAL PHYSICAL PROPERTIES	
Appearance	Clear, colorless liquid
Texture	Thin film
Flash Point Closed Cup (ASTM D 56) As Received	46°C (114°F)
Recommended Film Thickness Per Application Wet Dry	64 microns (2.5 mils) 36 microns (1.4 mils)
Coverage at 25 microns (1 mil) DFT	17m²/l (700 sq ft/gal)
Drying Time at 21°C (70°F) Tack Free/Complete	2 hours/12 - 24 hours
Application Temperature	10°C – 43°C (50°F – 110°F)
Service Temperature	-40°C – 79°C (-40°F – 175°F)
Flow Point	79°C (175°F)
Dry Film	154°C (310°F)
Auto Ignition Temperature (ASTM D 2155) As Received	254°C (490°F)
Weight Per Gallon	7.2 lbs
Density	0.9 kg/l
Percent Solids, Bulk By Volume/By Weight	44/50
Corrosion Protection Indoors/Outdoors	Long Term/2 Years under shed
Corrosion Resistance (ASTM B 117) 5% Salt Fog @ 38°C (100°F)	2000 hours



860 Salem Street, Groveland, MA 01834 USA 978-469-6888 chesterton.com

© 2018 A.W. Chesterton Company ® Registered trademark owned by A.W. Chesterton Company in USA and other countries, unless otherwise noted. Technical Data reflects results of laboratory tests and is intended to indicate general characteristics only. Since many actual application circumstances are beyond Chesterton's knowledge and/or control, the product user must determine the suitability of the products it intends to use for its particular purpose and assume all risks and liabilities in connection therewith. CHESTERTON DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form No. 071594 1/18